

Timber Hardened Wood Flooring

Pro Lacquer

Level of use domestic: **EN ISO 10874** Class Heavy Residential (Class 23)



Level of use commercial: **EN ISO 10874** Class Heavy Commercial (Class 33)



Construction: Engineered wood surface with cured wood composite core and wood backing
Surface Treatment: UV Cured Acrylic Pro Matte Laquer

General properties	Herringbone A + B
Thickness (mm/inches)	11/0.445
Width (mm/inches)	91/3.58
Length (mm/inches)	546/21.49
Wear layer thickness (mm/inches)	0.6/0.024
Micro bevel	long- and short side
Locking system	5G
Boards per box	22
m ² /sqft per box	1.09/11.73
m ² /sqft per pallet	52.47/564.8
Weight per m ² (kg/lbs)	11/24
Weight per box (kg/lbs)	12/26.5

Classification and safety properties	Standard test method	Result
Fire resistance	EN 13501	Bfl-S1 (hardly flammable)
Smoke density	ASTM E662	316 Flaming / 255 non-flaming
Critical radiant flux	ASTM E648	Class I - 0.82 W / cm ²
Thermal resistance	EN 12664 / 12667	R 0.07 (m ² x K)/W
Thermal conductivity	ASTM C518	1.2472 Vlu in. /h ft ² F
Formaldehyde emission	EN 717-1	E1
Carb Phase 2 Compliant	ASTM D6007-14	Yes
Brinell hardness	EN 1534	Herringbone 10 HB (average value)
Impact resistance	EN 14354	EC3
Thickness swell	EN 13329 / ISO 24336	Herringbone <8%
Taber abrasion resistance	EN 14354	>6000 revolutions
Sound transmission loss (STC) 8" slab only	ASTM E336/E413	55
Impact isolation class (IIC) 8" slab only	ASTM E492/E989	55
Slip resistance (COF)	ANSI A137.1/A326.3	wet: 0.73 (average value)

Installation properties	
Installation method	Floating or glue down application
Installation instructions	Download from www.endurematerials.com
Underlayment	Foam with CS > 60kPa & CC > 20 kPa (according to EN 16354)*
Care & maintenance Instructions	Download from www.endurematerials.com

* For demanding applications



Planet-Approved. Engineered to Last.TM
endurematerials.com 866-631-2221

